

Product Grade

MINIPAK

Mechanical Properties (Mean values)

Tensile Strength	EN ISO 10319	kN/m	7.5
Tensile Elongation	EN ISO 10319	%	60
CBR Puncture Resistance	EN ISO 12236	N	1350
Cone Drop	EN ISO 13433	mm	40

Hydraulic Properties (Mean values)

Permeability (H ₅₀)	EN ISO 11058	l/m ² .s	105
Opening Size (O ₉₀)	EN ISO 12956	μm	90

Physical Properties (Typical values)

Thickness at 2kPa	EN ISO 9863-1	mm	1.0
-------------------	---------------	----	-----

Pack Dimensions^(*)

Width		m	4.5
Length		m	11.1

Durability

This product is predicted to be durable for more than 25 years in soils with a pH in the range 2 to 14 and with a temperature of less than 25°C.

Chemical resistance

Terram standard geotextiles are unaffected by the chemicals which normally exist in soils.

UV exposure

Fiberweb Geosynthetics' products are delivered to site in polyethylene wrapping to protect against the effects of ultra-violet radiation. It is recommended that the products remain wrapped until their installation. Once unwrapped, the products should be completely covered with fill within 1 month to avoid exposure to UV radiation. Adequate precautions should always be taken to protect all products from UV radiation to achieve the stated durability.

Notes

1. Refer to the *Terram Jointing Methods* (downloadable from www.terram.com) for when simple overlaps are required for subsequent and adjacent roll lengths. However, pegging, sewing, stapling or gluing can also be used depending upon the application, the sub-grade conditions, the loading, the convenience and the cost.
2. These figures relate to standard product weights and roll sizes. Other weights, sizes and colours may be available on request. For further information please contact Fiberweb Geosynthetics' Technical Support.



For more information, contact us today or visit our website:
www.groundtrax.com

GROUNDTRAX
Ground Protection and Reinforcement
Telephone: 03456 800008 | Fax: 03456 800208
E-Mail: info@groundtrax.com | Website: www.groundtrax.com